

IN THE CLAIMS

Sub A6
1. A method for improving the environmental stress crack resistance of an elastomer-modified monovinylaromatic polymer material, comprising:

introducing a monovinylaromatic monomer feed stream into polymerization reactor;

introducing an elastomer feed stream into said polymerization reactor;

5 introducing a polymerization initiator compound into said reactor, said initiator

compound comprising at least one perketal and at least one peroxy carbonate; and

reacting said monomer, said initiator compound, and elastomer to form an elastomer-modified monovinylaromatic polymer having high ESCR value.

2. The method of claim 1 wherein said perketal is added in amounts of about 200 parts per million, by weight, and said peroxy carbonate is added in amounts ranging from about 150 to about 800 PPM, by weight.

Sub A7
3. The method of claim 1 wherein said perketal comprises Lupersol L-231 and said peroxy carbonate comprises t-Amyl 2-Ethylhexyl peroxy carbonate.

4. The method of claim 3 wherein said perketal is added in amounts of about 200 PPM by weight and said peroxy carbonate is added in amounts of about 400 PPM by weight.

5. The method of claim 4 further comprising adding to said reactor at least one chain transfer agent and at least one lubricant, said lubricant being selected from the group consisting of mineral oil and polyisobutylene.

Sub A8
6. The method of claim 5 wherein said chain transfer agent is a mercaptan, and is added in amounts of around 500 PPM, by weight.

7. The method of claim 5 wherein said lubricants added are mineral oil and polyisobutylene.

Sub A9

8. A process for producing cupgrade high impact polystyrene having improved gel content and grafting levels with reduced elastomer contents, aid process comprising:
introducing a styrene monomer feed stream into a polymerization reactor;
introducing a reduced-level elastomer feedstream into said reactor along with said styrene monomer feed;
introducing an initiator compound into said reactor, said compound comprising at least one perketal initiator and at least one peroxy-carbonate initiator; and,
reacting said feedstreams and initiator compound to produce impact resistant polystyrene.

9. The process of claim 8 wherein said perketal is Lupersol L-233 added in amounts of about 200 PPM, by weights, and said peroxy carbonate is TAEC in amounts of about 600 PPM, by weight.

Add A10

10052149-011702
202110-61125001